

Chevron Phillips HiD® 9301 HDPE Natural Pipe Resin (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Pipe Grade

Material Notes:

Resin Type: Linear Copolymer; PE2406 Pipe Resin; ASTM D 3350 Classification: 234360A; ASTM D 4976 Classification: PE 225, A

56607Applications:Base Resin for use in Gas, Oil Patch and Industrial Pipe Applications and FittingsData provided by Chevron Chemical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-HiD-9301-HDPE-Natural-Pipe-Resin-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.939 g/cc	0.0339 lb/in ³	ASTM D1505
Environmental Stress Crack Resistance	>= 2000 hour	>= 2000 hour	F₅₀, Cond. B.; ASTM D1693
	@Temperature 50.0 °C	@Temperature 122 °F	
	>= 5000 hour	>= 5000 hour	F₅₀ Cond. C; ASTM D 1693
	@Temperature 100 °C	@Temperature 212 °F	
Melt Flow	0.20 g/10 min	0.20 g/10 min	ASTM D 1238
	@Load 2.16 kg, Temperature 190 °C	@Load 4.76 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	63	63	ASTM D2240
Tensile Strength, Ultimate	31.0 MPa	4500 psi	ASTM D638
Tensile Strength, Yield	19.0 MPa	2760 psi	ASTM D638
Elongation at Break	>= 800 %	>= 800 %	ASTM D638
Flexural Modulus	0.790 GPa	115 ksi	3 pt. secant. ASTM D790

Thermal Properties	Metric	English	Comments
Vicat Softening Point	120 °C	248 °F	ASTM D1525
Brittleness Temperature	<= -59.0 °C	<= -74.2 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China