

Chevron Phillips Marlex® 9514H Polyethylene; HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE

Material Notes:

High density polyethylene. This gas phase, high molecular weight hexene copolymer is tailored for lightweight blow molded applications that: Require excellent stiffness to ESCR ratio Require good melt strength Are durable and recyclable for sustainability Applications: Typical blow molded applications for 9514H include: Household and industrial chemical containers Large parts Information provided by Phillips This resin meets these specifications: ASTM D4976 - PE 235 FDA 21 CFR 177.1520(c) 3.2a, use conditions B through H per 21 CFR 176.170(c)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-9514H-Polyethylene-HDPE.php

Physical Properties	Metric	English	Comments
Density	0.957 g/cc	0.0346 lb/in ³	ASTM D-1505
ESCR 100% Igepal®	50 hour	50 hour	Condition B, F50; ASTM D-1693
Melt Index of Compound	0.30 g/10 min @Load 2.16 kg, Temperature 190 °C	0.30 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.0 MPa	4350 psi	2 in/min, Type IV bar; ASTM D-638
Elongation at Break	800 %	800 %	2 in/min, Type IV bar; ASTM D-638
Flexural Modulus	1.41 GPa	205 ksi	Tangent - 16:1 span:depth, 0.5 in/min; ASTM D-790

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -75.0 °C	<= -103 °F	Type A, Type I specimen; ASTM D-746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China