

Chevron Phillips Marlex® B592 Polyethylene, Injection Molding Grade, HDPE (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

Material Notes:

Meets FDA Regulation 177.1520.Data provided by the manufacturer

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-Marlex-B592-Polyethylene-Injection-Molding-Grade-HDPE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.953 g/cc	0.0344 lb/in³	ASTM D1505
Melt Flow	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	ASTM D638
Elongation at Break	>= 400 %	>= 400 %	ASTM D638
Flexural Modulus	1.41 GPa	205 ksi	ASTM D790

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.33	2.33	ASTM D1531
	@Frequency 100000 Hz	@Frequency 100000 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149
	@Thickness 3.17 mm	@Thickness 0.125 in	
Dissipation Factor	>= 0.00010	>= 0.00010	ASTM D1531
	@Frequency 100000 Hz	@Frequency 100000 Hz	

Processing Properties	Metric	English	Comments
Processing Temperature	218 - 274 °C	424 - 525 °F	Stock Temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China