

Chevron Phillips Ryton® R10 5002C PPS Polyphenylene Sulfide (discontinued **)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

Ryton® PPS is used in many electronic and automotive applications because of its high strength, favorable electrical properties, and high temperature stability. Data provided by the manufacturer. Solvay Specialty Polymers has acquired the Ryton product line. This product was discontinued prior to the acquisition and is listed under the Chevron Phillips name for historical purposes.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chevron-Phillips-Ryton-R10-5002C-PPS-Polyphenylene-Sulfide-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in ³	ASTM D792
Water Absorption	0.070 %	0.070 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	117	117	
Tensile Strength, Ultimate	110 MPa	16000 psi	ASTM D638
Tensile Strength, Yield	110 MPa	16000 psi	ASTM D638
Elongation at Break	0.70 %	0.70 %	ASTM D638
Flexural Yield Strength	138 MPa	20000 psi	ASTM D790
Flexural Modulus	17.0 GPa	2470 ksi	ASTM D790
Compressive Yield Strength	128 MPa	18600 psi	ASTM D695
Shear Strength	76.0 MPa	11000 psi	ASTM D732
Izod Impact, Notched	0.530 J/cm	0.993 ft-lb/in	ASTM D256
Izod Impact, Unnotched	1.30 J/cm	2.44 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	0.770 J/g-°C	0.184 BTU/lb-°F	
	0.774 J/g-°C	0.185 BTU/lb-°F	
Thermal Conductivity	0.560 W/m-K	3.89 BTU-in/hr-ft ² -°F	
Melting Point	285 °C	545 °F	
	230 °C	446 °F	UL temperature Index 220/240°C

Maximum Service Temperature, Air Thermal Properties	Metric	English	(430/460°F) Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 260 °C	>= 500 °F	ASTM D648
Glass Transition Temp, Tg	88.0 °C	190 °F	
Flammability, UL94	5VA	5VA	V-0/5VA UL-94 Rating
Oxygen Index	53 %	53 %	ASTM D2863
	53 %	53 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	5.00e+15 ohm-cm	5.00e+15 ohm-cm	ASTM D257
Surface Resistance	2.00e+8 ohm @Temperature 90.0 °C	2.00e+8 ohm @Temperature 194 °F	95% RH, 48 hrs
Dielectric Constant	5.8 @Frequency 1000 Hz	5.8 @Frequency 1000 Hz	ASTM D150
	5.8 @Frequency 1e+6 Hz	5.8 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	13.0 kV/mm	330 kV/in	ASTM D149
Dissipation Factor	0.029 @Frequency 1e+6 Hz	0.029 @Frequency 1e+6 Hz	ASTM D150
	0.030 @Frequency 1000 Hz	0.030 @Frequency 1000 Hz	ASTM D150
Arc Resistance	116 sec	116 sec	ASTM D495
Comparative Tracking Index	160 V	160 V	UL 746A

Processing Properties	Metric	English	Comments
Melt Temperature	304 - 343 °C	579 - 649 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China