

## ChevronTexaco Rykotac® Grease EP

Category : Fluid , Lubricant , Urea Gellant

### Material Notes:

**Features**Chevron Rykotac Grease EP is manufactured using highly refined, select high viscosity index base oils, and a polyurea thickener. It is red in color and tacky in texture.Chevron Rykotac Grease EP contains polyurea thickener, highly refined paraffinic base oil, extreme pressure agents, and a special combination of synthetic tackiness agents. These agents allow maximum tackiness with a wide temperature range for high and low temperature performance.**Applications**Chevron Rykotac Grease EP is an excellent choice for heavy duty construction equipment, fifth wheel, chain drives, and other applications in which a grease that clings to metal and resists spin-off is needed. These properties are given by a formulation balanced to provide good cold weather and high temperature performance.Chevron Rykotac Grease EP can be used in both plain and antifriction bearings.**Applications include:**Cement plantsConstructionFarmingMarineMiningOil fieldsPaper millsGeneral industryConveyor systems

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ChevronTexaco-Rykotac-Grease-EP.php](http://www.lookpolymers.com/polymer_ChevronTexaco-Rykotac-Grease-EP.php)

Physical Properties	Metric	English	Comments
Viscosity Measurement	171	171	Viscosity Index; ASTM D2270
Saybolt Viscosity at 100°F	741 SUS	741 SUS	
Saybolt Viscosity at 210°F	106 SUS	106 SUS	
Kinematic Viscosity at 40°C (104°F)	145 cSt	145 cSt	ASTM D445
Kinematic Viscosity at 100°C (212°F)	21 cSt	21 cSt	ASTM D445

Mechanical Properties	Metric	English	Comments
Penetration	260	260	Worked

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	177 °C	351 °F	
Minimum Service Temperature, Air	-34.0 °C	-29.2 °F	
Dropping Point	260 °C	500 °F	

Descriptive Properties	Value	Comments
Color	Red	
Texture	Tacky	
Thickener, % / type	- / Polyurea	
Water Resistance, 79°C, % loss	2	

Descriptive Properties	Value	Comments
------------------------	-------	----------

**Contact Songhan Plastic Technology Co.,Ltd.**

Website : [www.lookpolymers.com](http://www.lookpolymers.com)  
Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)  
Tel : +86 021-51131842  
Mobile : +86 13061808058  
Skype : lookpolymers  
Address : United North Road 215,Fengxian District, Shanghai City,China