

ChevronTexaco Thuban® SAE 80W-90

Category : Fluid , Lubricant

Material Notes:

Typical test data are average values only. Minor variations which do not affect product performance are to be expected in normal manufacturing. CPS Number: 220993; MSDS Number: 8801

Order this product through the following link:

http://www.lookpolymers.com/polymer_ChevronTexaco-Thuban-SAE-80W-90.php

Physical Properties	Metric	English	Comments
API Gravity	29.9 °	29.9 °	
Viscosity Measurement	98	98	Viscosity Index
Saybolt Viscosity at 100°F	761 SUS	761 SUS	
Saybolt Viscosity at 210°F	77.7 SUS	77.7 SUS	
Kinematic Viscosity at 40°C (104°F)	145.2 cSt	145.2 cSt	
Kinematic Viscosity at 100°C (212°F)	14.5 cSt	14.5 cSt	

Thermal Properties	Metric	English	Comments
Pour Point	-30.0 °C	-22.0 °F	
Flash Point	282 °C	540 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China