

Chi Mei Kibiton® PB-5925 SBC

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene-Butadiene Copolymer, SBC

Material Notes:

Transparency, high stiffness, injection grade

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chi-Mei-Kibiton-PB-5925-SBC.php

Physical Properties	Metric	English	Comments
Density	1.01 g/cc	0.0365 lb/in ³	ISO 1183
Melt Flow	11 g/10 min	11 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	72	72	
Tensile Strength at Break	19.0 MPa	2760 psi	50 mm/min, 4 mm; ISO 527
Tensile Strength, Yield	32.0 MPa	4640 psi	50 mm/min, 4 mm; ISO 527
Elongation at Break	43 %	43 %	50 mm/min, 4mm; ISO 527
Elongation at Yield	2.0 %	2.0 %	50 mm/min, 4 mm; ISO 527
Flexural Strength	43.0 MPa	6240 psi	2 mm/min, 4 mm; ISO 178
Flexural Modulus	1.80 GPa	261 ksi	2 mm/min, 4 mm; ISO 178
Izod Impact, Notched	0.246 J/cm	0.460 ft-lb/in	ASTM D256
	@Thickness 6.35 mm, Temperature 23.0 °C	@Thickness 0.250 in, Temperature 73.4 °F	
Izod Impact, Notched (ISO)	2.30 kJ/m ²	1.09 ft-lb/in ²	ISO 180/1A
Charpy Impact Unnotched	1.30 J/cm ²	6.19 ft-lb/in ²	ISO 179
Charpy Impact, Notched	0.260 J/cm ²	1.24 ft-lb/in ²	ISO 179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	71.0 °C	160 °F	unannealed; ISO 75
	83.0 °C	181 °F	annealed; ISO 75
Vicat Softening Point	73.0 °C	163 °F	120°C/hr; ISO 306

Thermal Properties	@Load 5.00 kg Metric	@Load 11.0 lb English	Comments
	75.0 °C	167 °F	50°C/hr; ISO 306
	@Load 5.00 kg	@Load 11.0 lb	
	92.0 °C	198 °F	120°C/hr; ISO 306
	@Load 1.00 kg	@Load 2.20 lb	
	95.0 °C	203 °F	50°C/hr; ISO 306
	@Load 1.00 kg	@Load 2.20 lb	

Optical Properties	Metric	English	Comments
Haze	2.5 %	2.5 %	ASTM D1003
	@Thickness 3.17 mm	@Thickness 0.125 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China