

Chi Mei Polylac® PA-746 ABS - High Flow

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

High flow, medium impact

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chi-Mei-Polylac-PA-746-ABS-High-Flow.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
Melt Flow	3.0 g/10 min	3.0 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	34 g/10 min	34 g/10 min	ISO-1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	108	108	ASTM D785
Ball Indentation Hardness	88.0 MPa	12800 psi	H358/30; ISO 2039-1
Tensile Strength at Break	32.0 MPa	4640 psi	50 mm/min; ISO 527
Tensile Strength, Yield	43.0 MPa	6240 psi	50 mm/min; ISO 527
Elongation at Break	15 %	15 %	50 mm/min; ISO 527
Flexural Strength	60.0 MPa	8700 psi	2 mm/min; ISO 178
Flexural Modulus	1.80 GPa	261 ksi	2 mm/min; ISO 178
Izod Impact, Notched	2.66 J/cm	4.98 ft-lb/in	ASTM D256
	@Thickness 6.35 mm	@Thickness 0.250 in	
	3.32 J/cm	6.22 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Izod Impact, Notched (ISO)	22.0 kJ/m ²	10.5 ft-lb/in ²	ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	ISO 180/1C
Charpy Impact Unnotched	NB	NB	ISO 179

Charpy Impact, Notched Mechanical Properties	2.50 J/cm ² Metric	11.9 ft-lb/in ² English	ISO 179 Comments
Impact	17.0	17.0	Impact Flexural Test Notched (KJ/m ²)
	NB	NB	Impact Flexural Test Unnotched (KJ/m ²)

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	87.0 °C	189 °F	unannealed; ISO 75
	96.0 °C	205 °F	annealed; ISO 75
Vicat Softening Point	94.0 °C @Load 5.00 kg	201 °F @Load 11.0 lb	50°C/hr; ISO 306
	95.0 °C @Load 5.00 kg	203 °F @Load 11.0 lb	120°C/hr; ISO 306
	102 °C @Load 1.00 kg	216 °F @Load 2.20 lb	50°C/hr; ISO 306
	103 °C @Load 1.00 kg	217 °F @Load 2.20 lb	120°C/hr; ISO 306
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	UL 94

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China