

Chosun Refractories CT- 130 Fireclay Castables

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-CT-130-Fireclay-Castables.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.0024525 GPa	0.35571 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.0024525 - 0.0063765 GPa	0.35571 - 0.92485 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
Compressive Strength	9.81 - 19.6 MPa	1420 - 2840 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	14.7 MPa	2130 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.60484 W/m-K	4.1908 BTU-in/hr-ft ² -°F	
	@Temperature 260 °C	@Temperature 500 °F	
	0.66300 W/m-K	4.5938 BTU-in/hr-ft ² -°F	
	@Temperature 540 °C	@Temperature 1000 °F	
	0.7560 W/m-K	5.238 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	
Maximum Service Temperature, Air	1300 °C	2370 °F	limited
Shrinkage	-0.600 %	-0.600 %	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
	-0.120 %	-0.120 %	
	@Temperature 110 °C,	@Temperature 230 °F,	

Thermal Properties	Time 86400 sec Metric	Time 24.0 hour English	Comments
Component Elements Properties	Metric	English	Comments
Al2O3	33 %	33 %	
SiO2	60 %	60 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Troweling	
Material Required for Estimating(kg/?)	1,800	
Water Required for Casting(%)	14.0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China