

Chosun Refractories CT-140S Fireclay Castables

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-CT-140S-Fireclay-Castables.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.002943 - 0.006867 GPa	0.4269 - 0.9960 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	0.002943 - 0.007848 GPa	0.4269 - 1.138 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.003924 - 0.008829 GPa	0.5691 - 1.281 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
Compressive Strength	19.6 - 29.4 MPa	2840 - 4270 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
	24.5 - 34.3 MPa	3560 - 4980 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	29.4 - 39.2 MPa	4270 - 5690 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.5234 W/m-K	3.627 BTU-in/hr-ft ² -°F	
	@Temperature 260 °C	@Temperature 500 °F	
	0.65137 W/m-K	4.5132 BTU-in/hr-ft ² -°F	
	@Temperature 540 °C	@Temperature 1000 °F	
	0.77931 W/m-K	5.3997 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1350 °C	2460 °F	
Shrinkage	-1.20 % @Temperature 1350 °C, Time 10800 sec	-1.20 % @Temperature 2460 °F, Time 3.00 hour	
	-0.0900 % @Temperature 110 °C, Time 86400 sec	-0.0900 % @Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	43 %	43 %	
SiO2	44 %	44 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Troweling	
Material Required for Estimating(kg/?)	2,000	
Water Required for Casting(%)	11.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China