

Chosun Refractories INCT-140 Light-Weight Castable

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-INCT-140-Light-Weight-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	4.33e-7 - 0.00147 GPa	0.0000628 - 0.213 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.0014715 - 0.0044145 GPa	0.21343 - 0.64028 ksi	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	0.0014715 - 0.0044145 GPa	0.21343 - 0.64028 ksi	
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	
Compressive Strength	4.90 - 14.7 MPa	711 - 2130 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	4.90 - 14.7 MPa	711 - 2130 psi	Cold Crushing Strength
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
	4.90 - 14.7 MPa	711 - 2130 psi	Cold Crushing Strength
	@Temperature 1000 °C, Time 10800 sec	@Temperature 1830 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.3955 W/m-K	2.740 BTU-in/hr-ft ² -°F	
	@Temperature 260 °C	@Temperature 500 °F	
	0.44200 W/m-K	3.0625 BTU-in/hr-ft ² -°F	
	@Temperature 540 °C	@Temperature 1000 °F	
	0.48852 W/m-K	3.3849 BTU-in/hr-ft ² -°F	
	@Temperature 800 °C	@Temperature 1470 °F	

Maximum Service Temperature, Air Thermal Properties	1400 °C Metric	2550 °F English	limited Comments
Shrinkage	-0.250 % @Temperature 1000 °C, Time 10800 sec	-0.250 % @Temperature 1830 °F, Time 3.00 hour	
	-0.0600 % @Temperature 110 °C, Time 86400 sec	-0.0600 % @Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	50 %	50 %	
SiO2	36 %	36 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Troweling	
Main Applications	Fireproof insulating castable	
Material Required for Estimating (kg/?)	1,350	
Water Required for Casting(%)	25-30	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China