

Chosun Refractories INCT-50S Light-Weight Castable

Category : Ceramic

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-INCT-50S-Light-Weight-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	9.62361e-8 - 0.0004905 GPa	0.0000139581 - 0.07114 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.0004905 - 0.000981 GPa	0.07114 - 0.142 ksi	
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	
Compressive Strength	2.94 - 3.92 MPa	427 - 569 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	2.94 - 3.92 MPa	427 - 569 psi	Cold Crushing Strength
	@Temperature 500 °C, Time 10800 sec	@Temperature 932 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.2210 W/m-K	1.531 BTU-in/hr-ft ² -°F	
	@Temperature 540 °C	@Temperature 1000 °F	
Maximum Service Temperature, Air	500 °C	932 °F	limited
Shrinkage	-0.700 %	-0.700 %	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	-0.0600 %	-0.0600 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	

Component Elements Properties	Metric	English	Comments
Al2O3	33 %	33 %	
SiO2	33 %	33 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Troweling	
Main Applications	Duct	
Material Required for Estimating (kg/?)	900	
Water Required for Casting(%)	60-70	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China