

Chosun Refractories MMCT-75 Special Castable

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-MMCT-75-Special-Castable.php

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.006867 GPa	0.9960 ksi	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.00981 GPa	1.42 ksi	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	0.01962 GPa	2.846 ksi	
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	
Compressive Strength	34.3 MPa	4980 psi	Cold Crushing Strength
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	58.8 MPa	8530 psi	Cold Crushing Strength
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	88.3 MPa	12800 psi	Cold Crushing Strength
	@Temperature 1500 °C, Time 10800 sec	@Temperature 2730 °F, Time 3.00 hour	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	1600 °C	2910 °F	limited
Shrinkage	-0.150 %	-0.150 %	
	@Temperature 1350 °C, Time 10800 sec	@Temperature 2460 °F, Time 3.00 hour	
	-0.0600 %	-0.0600 %	
	@Temperature 110 °C, Time 86400 sec	@Temperature 230 °F, Time 24.0 hour	
	0.30 %	0.30 %	
	@Temperature 1500 °C,	@Temperature 2730 °F,	

Thermal Properties	Time 10800 sec Metric	Time 3.00 hour English	Comments
Component Elements Properties	Metric	English	Comments
Al2O3	75 %	75 %	
SiO2	10 %	10 %	

Descriptive Properties	Value	Comments
Installation Method	Casting, Vibrating	
Material Required for Estimating(kg/?)	2,500	
Water Required for Casting(%)	8.0	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China