

Chosun Refractories SAL90 Special High Alumina brick

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Information provided by Chosun Refractories via Korea Institute of Ceramic Engineering and Technology (KICET).

Order this product through the following link:

http://www.lookpolymers.com/polymer_Chosun-Refractories-SAL90-Special-High-Alumina-brick.php

Physical Properties	Metric	English	Comments
Bulk Density	3.10 g/cc	0.112 lb/in ³	
Porosity	15 %	15 %	

Mechanical Properties	Metric	English	Comments
Compressive Strength	88.3 MPa	12800 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
CTE, linear	7.00 µm/m-°C	3.89 µin/in-°F	
	@Temperature 1000 °C	@Temperature 1830 °F	
Shrinkage	0.00 %	0.00 %	
	@Temperature 1500 °C, Time 7200 sec	@Temperature 2730 °F, Time 2.00 hour	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	91 %	91 %	
Cr ₂ O ₃	0.30 %	0.30 %	

Descriptive Properties	Value	Comments
Chemical Analysis(%),Fe ₂ O ₃	Hot blast stove,Electric kiln, Reheating furnace, Cupolar, Various High-temp. furnace	
Refractories Under Load(2kg/?,T2?)	1,700 T2	
Refractoriness (SK)	40	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China