

Clariant Renol 66G15BL-195 Blue Nylon 66, 15% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 20% Glass Fiber Filled

Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

http://www.lookpolymers.com/polymer_Clariant-Renol-66G15BL-195-Blue-Nylon-66-15-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	96.5 MPa	14000 psi	ASTM D638
Elongation at Yield	3.0 %	3.0 %	ASTM D638
Flexural Yield Strength	152 MPa	22000 psi	ASTM D790
Flexural Modulus	4.62 GPa	670 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm @Temperature 22.8 °C	0.800 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	243 °C	470 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	235 °C	455 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	271 - 293 °C	520 - 560 °F	
Mold Temperature	79.4 - 93.3 °C	175 - 200 °F	
Dry Time	2 - 4 hour @Temperature 71.1 °C	2 - 4 hour @Temperature 160 °F	to eliminate surface defects
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.000 - 0.345 MPa	0.000 - 50.0 psi	

Shot Size Processing Properties	30 - 80 % Metric	30 - 80 % English	Comments
Screw Speed	20 - 100 rpm	20 - 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China