

Clariant Renol ABS3470 ABS, High Heat, Low Gloss

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

http://www.lookpolymers.com/polymer_Clariant-Renol-ABS3470-ABS-High-Heat-Low-Gloss.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	39.3 MPa	5700 psi	ASTM D638
Elongation at Yield	40 %	40 %	ASTM D638
Flexural Modulus	2.07 GPa	300 ksi	ASTM D790
Izod Impact, Notched	1.60 J/cm @Temperature 22.8 °C	3.00 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	98.9 °C	210 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	216 - 249 °C	420 - 480 °F	
Mold Temperature	65.6 - 93.3 °C	150 - 200 °F	
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.345 - 1.72 MPa	50.0 - 250 psi	
Shot Size	30 - 80 %	30 - 80 %	
Screw Speed	20 - 100 rpm	20 - 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China