

Clariant Renol PCSP0013WT-192 Polycarbonate, Flame Retardant, UV Stabilized, High Opacity

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Unreinforced, Flame Retardant , Polycarbonate, UV Stabilized

Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

http://www.lookpolymers.com/polymer_Clariant-Renol-PCSP0013WT-192-Polycarbonate-Flame-Retardant-UV-Stabilized-High-Opacity.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc	1.55 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	49.6 MPa	7200 psi	ASTM D638
Flexural Yield Strength	100 MPa	14500 psi	ASTM D790
Flexural Modulus	3.96 GPa	575 ksi	ASTM D790
Izod Impact, Notched	3.84 J/cm @Temperature 22.8 °C	7.20 ft-lb/in @Temperature 73.0 °F	ASTM D256

Processing Properties	Metric	English	Comments
Melt Temperature	271 - 299 °C	520 - 570 °F	
Mold Temperature	65.6 - 79.4 °C	150 - 175 °F	
Dry Time	2 - 4 hour @Temperature 104 °C	2 - 4 hour @Temperature 220 °F	to ensure moisture content is less than 0.05%
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.345 - 1.72 MPa	50.0 - 250 psi	
Shot Size	30 - 80 %	30 - 80 %	
Screw Speed	20 - 100 rpm	20 - 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China