

Clariant Renol PPSP0005 Polypropylene Homopolymer, Glass Fiber and Mica Reinforced, Chemically Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Data provided by Clariant Masterbatches

Order this product through the following link:

http://www.lookpolymers.com/polymer_Clariant-Renol-PPSP0005-Polypropylene-Homopolymer-Glass-Fiber-and-Mica-Reinforced-Chemically-Coupled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.03 g/cc	1.03 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	46.9 MPa	6800 psi	ASTM D638
Flexural Yield Strength	65.5 MPa	9500 psi	ASTM D790
Flexural Modulus	3.24 GPa	470 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm @Temperature 22.8 °C	0.700 ft-lb/in @Temperature 73.0 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	130 °C	266 °F	ASTM D648

Processing Properties	Metric	English	Comments
Melt Temperature	191 - 221 °C	375 - 430 °F	
Mold Temperature	51.7 - 79.4 °C	125 - 175 °F	
Injection Pressure	4.96 - 8.27 MPa	720 - 1200 psi	Secondary
	8.27 - 13.8 MPa	1200 - 2000 psi	Initial
Back Pressure	0.345 - 1.72 MPa	50.0 - 250 psi	
Shot Size	30 - 80 %	30 - 80 %	
Screw Speed	20 - 100 rpm	20 - 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China