

Colorite Polymers Elastichem 5511TX-02 Vinyl Compound

Category: Polymer, Thermoplastic, Vinyl (PVC), PVC, Molded

Material Notes:

Description: All components in Elastichem are sanctioned by the U.S. Food & Drug Administration for food packaging applications under Title 21 of the Code of Federal Regulations. For medical use, complete traceability and lot identification of all components are maintained at Colorite. Low coefficient of friction Low gels Improved physical properties Non-sticking, even at 40 shore ASelf-frosting for extrusion Self-frosting for injection molding Excellent resiliency for product requiring peristaltic motion Improved extrusion rates for low durometer compounds (i.e. 40-50A) Information provided by Colorite Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Colorite-Polymers-Elastichem-5511TX-02-Vinyl-Compound.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|-----------|
| Specific Gravity | 1.18 g/cc | 1.18 g/cc | ASTM D792 |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-------------|-----------|------------|
| Hardness, Shore A | 55 | 55 | ASTM D2240 |
| Tensile Strength, Ultimate | 12.3 MPa | 1790 psi | ASTM D638 |
| Elongation at Break | 465 % | 465 % | ASTM D638 |
| Modulus of Elasticity | 0.00314 GPa | 0.455 ksi | ASTM D638 |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|----------|----------|-----------------------------|
| Minimum Service Temperature, Air | -47.0 °C | -52.6 °F | T _f ; ASTM D746 |
| Brittleness Temperature | -55.0 °C | -67.0 °F | XT _b ; ASTM D746 |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China