

Cookson Group Plaskon® ULS-12 Epoxy Encapsulant (discontinued **)

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Test specimens were transfer molded and post cured 4 hours at 175°C. A state-of-the-art, ultra low stress epoxy encapsulant designed for packaging large, stress-sensitive DIPs, PLCCs and QFPs. It is formulated with a unique filler system that reduces the expansion coefficient without compromising moldability. Ultra low stress properties; Outstanding moldability (good mold filling, low wire sweep, fast cycles and good hot hardness); Superior reliability

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cookson-Group-Plaskon-ULS-12-Epoxy-Encapsulant-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.88 g/cc	0.0679 lb/in ³	
Water Absorption	0.0034 %	0.0034 %	
Viscosity	5500 cP @Temperature 175 °C	5500 cP @Temperature 347 °F	Automatic orifice Viscosity
Linear Mold Shrinkage	0.0025 cm/cm	0.0025 in/in	
Spiral Flow	81.0 cm	31.9 in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	80	80	
Flexural Strength	107 MPa	15500 psi	
Flexural Modulus	14.0 GPa	2030 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	12.5 µm/m-°C @Temperature 20.0 °C	6.94 µin/in-°F @Temperature 68.0 °F	
CTE, linear, Transverse to Flow	65.0 µm/m-°C @Temperature 20.0 °C	36.1 µin/in-°F @Temperature 68.0 °F	
Thermal Conductivity	0.700 W/m-K	4.86 BTU-in/hr-ft ² -°F	
Glass Transition Temp, Tg	168 °C	334 °F	
Flammability, UL94	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	
	V-0	V-0	

Thermal Properties	Metric	English	Comments
	@ Thickness 3.20 mm	@ Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.8	3.8	
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dielectric Strength	16.0 kV/mm	406 kV/in	
Dissipation Factor	0.0020	0.0020	
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Arc Resistance	180 sec	180 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	170 - 185 °C	338 - 365 °F	Molding temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China