

CoorsTek AD-96 Alumina (nom. 96% Al₂O₃)

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Thermal Shock Delta Tc = 250°C - Thermal shock tests are performed by quenching samples in water from different elevated temperatures. Delta Tc is the change in temperature which results in a sharp decrease in the flexural strength of the sample. Corrosion: Although all Coors Ceramics are highly resistant to chemical attack, Coors recommends obtaining specific application data from Coors before design finalization. Data Provided by the manufacturer, Coors Ceramics Co.

Order this product through the following link:

[http://www.lookpolymers.com/polymer_CoorsTek-AD-96-Alumina-nom-96-Al₂O₃.php](http://www.lookpolymers.com/polymer_CoorsTek-AD-96-Alumina-nom-96-Al2O3.php)

Physical Properties	Metric	English	Comments
Density	3.72 g/cc	0.134 lb/in ³	ASTM C20
Water Absorption	0.00 %	0.00 %	ASTM C373
Particle Size	6.0 µm	6.0 µm	Average Crystal Size - Thin Section Test

Mechanical Properties	Metric	English	Comments
Knoop Microhardness	11.5	11.5	1000 g load
Hardness, Rockwell 45 N	78	78	GPa
Tensile Strength, Ultimate	221 MPa	32100 psi	ACMA Test #4
Modulus of Elasticity	303 GPa	43900 ksi	ASTM C848
Flexural Strength	358 MPa	51900 psi	ASTM F417
Compressive Strength	2068 MPa	299900 psi	ASTM C773
Poissons Ratio	0.21	0.21	ASTM C848
Fracture Toughness	4.00 - 5.00 MPa-m ^{1/2}	3.64 - 4.55 ksi-in ^{1/2}	
Shear Modulus	125 GPa	18100 ksi	Calculated

Thermal Properties	Metric	English	Comments
CTE, linear	8.20 µm/m-°C @Temperature 25.0 - 1000 °C	4.56 µin/in-°F @Temperature 77.0 - 1830 °F	ASTM C372
Specific Heat Capacity	0.880 J/g-°C	0.210 BTU/lb-°F	ASTM E1269
Thermal Conductivity	24.7 W/m-K	171 BTU-in/hr-ft ² -°F	ASTM C408

Maximum Service Temperature, Air Thermal Properties	1700 °C Metric	3090 °F English	No Load Comments
---	-------------------	--------------------	---------------------

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00\text{e}+14$ ohm-cm	$\geq 1.00\text{e}+14$ ohm-cm	ASTM D1829
	1.00e+6 ohm-cm	1.00e+6 ohm-cm	ASTM D1829
	@Temperature 1000 °C	@Temperature 1830 °F	
	4.00e+9 ohm-cm	4.00e+9 ohm-cm	ASTM D1829
	@Temperature 500 °C	@Temperature 932 °F	
Dielectric Constant	9.0	9.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	8.30 kV/mm	211 kV/in	ac; ASTM D116
Dielectric Loss Index	0.00020	0.00020	at 25°C, 1 MHz; ASTM D2520

Descriptive Properties	Value	Comments
Color	White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China