

Cosmic Plastics 224 Dacron Filled Ortho Diallyl Phthalate Molding Compound

Category : Polymer , Thermoset , Diallyl Phthalate (DAP) , Diallyl Phthalate (DAP), Molded, Fiber Filled , Filled/Reinforced Thermoset

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cosmic-Plastics-224-Dacron-Filled-Ortho-Diallyl-Phthalate-Molding-Compound.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	
Apparent Bulk Density	0.270 g/cc	0.00975 lb/in ³	
Water Absorption	0.35 %	0.35 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	25.0 - 36.0 MPa	3630 - 5220 psi	
Flexural Strength	76.0 MPa	11000 psi	
Compressive Strength	141 MPa	20500 psi	
Izod Impact, Notched	1.60 J/cm	3.00 ft-lb/in	

Thermal Properties	Metric	English	Comments
CTE, linear	40.0 µm/m-°C	22.2 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 1.8 MPa (264 psi)	143 °C	289 °F	Heat Distortion temperature
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+17 ohm-cm	>= 1.00e+17 ohm-cm	
Surface Resistance	>= 1.00e+17 ohm	>= 1.00e+17 ohm	
Dielectric Constant	3.5	3.5	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	3.6	3.6	

Electrical Properties	Metric @Frequency 1e+6 Hz	English @Frequency 1e+6 Hz	Wet Comments
Dielectric Strength	14.0 kV/mm	356 kV/in	Wet, Step by Step
Dissipation Factor	0.0080	0.0080	Wet
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.012	0.012	Wet
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Arc Resistance	125 sec	125 sec	

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China