

## Cosmic Plastics CP7311 Epoxy Molding Compound

Category : Polymer , Thermoset , Epoxy , Epoxy Molding Compound

**Material Notes:**

Data provided by the manufacturer.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Cosmic-Plastics-CP7311-Epoxy-Molding-Compound.php](http://www.lookpolymers.com/polymer_Cosmic-Plastics-CP7311-Epoxy-Molding-Compound.php)

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in <sup>3</sup>	
Water Absorption	0.20 %	0.20 %	48 hrs, 50°C
Linear Mold Shrinkage	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	typical.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	138 - 207 MPa	20000 - 30000 psi	
Flexural Strength	345 MPa	50000 psi	
Compressive Strength	241 MPa	35000 psi	
Izod Impact, Notched	21.0 J/cm	39.3 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	243 °C	469 °F	Heat Distortion temperature

Processing Properties	Metric	English	Comments
Processing Temperature	135 - 165 °C	275 - 329 °F	Molding temperature

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China