

Cossa Polimeri ESTAPROP 1040 T8 V0 Flame Retardant Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Flame Retardant

Material Notes:

Flame retardant class V0, good mechanical characteristics Information provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-1040-T8-V0-Flame-Retardant-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in³	ASTM D 792
Linear Mold Shrinkage	0.0090 - 0.010 cm/cm	0.0090 - 0.010 in/in	ASTM D 955
Melt Flow	10 g/10 min @Load 2.16 kg, Temperature 230 °C	10 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	20.0 MPa	2900 psi	ASTM D 638
Elongation at Break	10 %	10 %	ASTM D 638
Flexural Modulus	3.30 GPa	479 ksi	ASTM D 790
Izod Impact, Notched	0.200 J/cm @Temperature 0.000 °C	0.375 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.300 J/cm @Temperature 23.0 °C	0.562 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	65.0 °C	149 °F	120°C/hr; ASTM D 648
Vicat Softening Point	150 °C @Load 0.999 kg	302 °F @Load 2.20 lb	50°C/hr; ASTM D 1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	
Glow Wire Test	960 °C @Thickness 2.00 mm	1760 °F @Thickness 0.0787 in	I.E.C. 695-2-1

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China