

Cossa Polimeri ESTAPROP H 2550 CBS/E Polypropylene, 25% Mineral Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Mineral Reinforced

Material Notes:

PP homopolymer 25% mineral fillerHigh gloss, very high melt flow rate, excellent processabilityInformation provided by Cossa Polimeri S.r.l.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Cossa-Polimeri-ESTAPROP-H-2550-CBSE-Polypropylene-25-Mineral-Filled.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D 792
Linear Mold Shrinkage	0.011 - 0.013 cm/cm	0.011 - 0.013 in/in	ASTM D 955
Melt Flow	30 g/10 min @Load 2.16 kg, Temperature 230 °C	30 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	23.0 MPa	3340 psi	ASTM D 638
Tensile Strength, Yield	27.0 MPa	3920 psi	ASTM D 638
Elongation at Break	50 %	50 %	ASTM D 638
Tensile Modulus	2.20 GPa	319 ksi	ASTM D 638
Flexural Modulus	2.00 GPa	290 ksi	ASTM D 790
Izod Impact, Notched	0.150 J/cm @Temperature -20.0 °C	0.281 ft-lb/in @Temperature -4.00 °F	ASTM D 638
	0.250 J/cm @Temperature 0.000 °C	0.468 ft-lb/in @Temperature 32.0 °F	ASTM D 638
	0.350 J/cm @Temperature 23.0 °C	0.656 ft-lb/in @Temperature 73.4 °F	ASTM D 256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	120°C/hr; ASTM D 648
Vicat Softening Point	95.0 °C @Load 5.00 kg	203 °F @Load 11.0 lb	50°C/hr; ASTM D 1525
	HB	HB	

Flammability: UL 94 Thermal Properties		Metric @ Thickness 1.60 mm	English @ Thickness 0.0630 in	Comments
		HB	HB	
		@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China