

Covestro Bayblend® FR3012 PC/ABS Blend

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Main characteristics:• High toughness even at low temperatures• High dimensional accuracy and stability• Good paintability• Good flowability
Grade characteristics:• Flame-retardant• Injection molding
As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Bayblend-FR3012-PCABS-Blend.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183-1
Moisture Absorption at Equilibrium	0.20 %	0.20 %	ISO 62, 50% RH
Water Absorption at Saturation	0.50 %	0.50 %	ISO 62
Viscosity	155000 cP @Shear Rate 1000 1/s, Temperature 260 °C	155000 cP @Shear Rate 1000 1/s, Temperature 500 °F	melt viscosity; b.o. ISO 11443-A
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.00 mm	0.0050 - 0.0070 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577
Linear Mold Shrinkage, Transverse	0.0050 - 0.0070 cm/cm @Thickness 3.00 mm	0.0050 - 0.0070 in/in @Thickness 0.118 in	150x105x3mm; b.o. ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	45.0 MPa	6530 psi	50 mm/min; ISO 527-1,-2
Tensile Strength, Yield	60.0 MPa	8700 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 40 %	>= 40 %	50 mm/min; b.o. ISO 527-1,-2
Elongation at Yield	3.5 %	3.5 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.60 GPa	377 ksi	1 mm/min; ISO 527-1,-2
Izod Impact, Notched (ISO)	10.0 kJ/m ² @Temperature -30.0 °C	4.76 ft-lb/in ² @Temperature -22.0 °F	ISO 180-A
	20.0 kJ/m ² @Temperature 23.0 °C	9.52 ft-lb/in ² @Temperature 73.4 °F	ISO 180-A
Izod Impact, Unnotched (ISO)	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 180-U

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	76.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 23.0 - 55.0 °C	42.2 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 73.4 - 131 °F	ISO 11359-1,-2
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot\text{°C}$ @Temperature 23.0 - 55.0 °C	44.4 $\mu\text{in}/\text{in}\cdot\text{°F}$ @Temperature 73.4 - 131 °F	ISO 11359-1,-2
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ISO 75-1,-2
Vicat Softening Point	100 °C @Load 5.10 kg	212 °F @Load 11.2 lb	50 $\text{°C}/\text{h}$; ISO 306
	102 °C @Load 5.10 kg	216 °F @Load 11.2 lb	120 $\text{°C}/\text{h}$; ISO 306
Flammability, UL94	V-1 @Thickness 1.50 mm	V-1 @Thickness 0.0591 in	
	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Melt Temperature	240 °C	464 °F	Injection molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection molding; ISO 294
Injection Velocity	240 mm/sec	9.45 in/sec	ISO 294

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China