

Covestro Baydur® 730 IBS Polyurethane Structural Foam RIM, Density 35 pcf, MDI-based 2-Component Liquid System

Category : Other Engineering Material , Composite Core Material , Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

Material Notes:

0.25 in. thickness. IBS = Interactive Blowing System RIM = Reaction Injection Molding Information provided by Bayer Corporation, Polyurethanes Division As of 1 September 2015, Bayer Material Science was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Baydur-730-IBS-Polyurethane-Structural-Foam-RIM-Density-35-pcf-MDI-based-2-Component-Liquid-System.php

Physical Properties	Metric	English	Comments
Density	0.560 g/cc	0.0202 lb/in ³	ASTM D792
Apparent Bulk Density	0.560 g/cc	0.0202 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	Bayer Test

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	65	65	ASTM D2240
Tensile Strength, Ultimate	14.0 MPa	2030 psi	ASTM D638/D412
Elongation at Break	10 %	10 %	ASTM D638/D412
Flexural Yield Strength	28.0 MPa	4060 psi	ASTM D790
Flexural Modulus	0.870 GPa	126 ksi	ASTM D790
Compressive Yield Strength	14.0 MPa	2030 psi	ASTM D395
Charpy Impact, Notched	1.70 J/cm ²	8.09 ft-lb/in ²	Bayer Test

Thermal Properties	Metric	English	Comments
CTE, linear	79.0 µm/m-°C	43.9 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	70.0 °C	158 °F	ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 6.35 mm	@Thickness 0.250 in	
	HB	HB	

Thermal Properties	@Thickness 6.35 mm Metric	@Thickness 0.250 in English	Comments
--------------------	------------------------------	--------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China