

Covestro Desmopan® DP 2792A Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Coating gradedoes not contain any anti-hydrolysis agentfood contact applications are possiblecontact our HSEQ departmentApplicationTextile coatingPreprocessingMax. Water content

Order this product through the following link:
http://www.lookpolymers.com/polymer_Covestro-Desmopan-DP-2792A-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in³	Melt
	1.21 g/cc	0.0437 lb/in³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	3s; ISO 868
Hardness, Shore D	50	50	15s; ISO 868
Abrasion	70	70	mm³; ISO 4649
Compression Set	26 %	26 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	69 %	69 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.70 J/g-°C	0.406 BTU/lb-°F	Melt
Thermal Conductivity	0.139 W/m-K	0.965 BTU-in/hr-ft²-°F	Melt

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 220 °C	374 - 428 °F	
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	
Ejection Temperature	50.0 °C	122 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	

Descriptive Properties	Value	Comments
	Near East/Africa	
	South and Central America	
Eff. thermal diffusivity (m ² /s)	7.98E-08	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China