

Covestro Desmopan® DP 8795 A Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

injection molding gradewith special UV stabilizersEasy releaseshort cycle timesApplicationSports shoe solesPreprocessingMax. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Desmopan-DP-8795-A-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.21 g/cc	0.0437 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	3s; ISO 868
Hardness, Shore D	41	41	15s; ISO 868
Abrasion	26	26	mm ³ ; ISO 4649
Compression Set	20 %	20 %	ISO 815
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	40 %	40 %	ISO 815
	@Temperature 70.0 °C	@Temperature 158 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	India	
	Near East/Africa	
	South and Central America	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

