

Covestro Desmopan® DP 9662DU Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Extrusion- and injection molding grade with special UV stabilizer transparent up to 6 mm wall thickness very good hydrolysis and microbial resistance
Application Ski boot shells Hoses non-reinforced Preprocessing Max. Water content

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Desmopan-DP-9662DU-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	0.985 g/cc	0.0356 lb/in ³	Melt
	1.18 g/cc	0.0426 lb/in ³	ISO 1183

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	97	97	3s; ISO 868
Hardness, Shore D	62	62	15s; ISO 868
Abrasion	20	20	mm ³ ; ISO 4649
Compression Set	59 % @Temperature 23.0 °C	59 % @Temperature 73.4 °F	ISO 815
	87 % @Temperature 70.0 °C	87 % @Temperature 158 °F	ISO 815

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	1.70 J/g-°C	0.406 BTU/lb-°F	Melt
Thermal Conductivity	0.134 W/m-K	0.930 BTU-in/hr-ft ² -°F	Melt

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 240 °C	428 - 464 °F	
Mold Temperature	20.0 - 40.0 °C	68.0 - 104 °F	
Ejection Temperature	50.0 °C	122 °F	

Descriptive Properties	Value	Comments
Availability	Asia Pacific	
	Europe	
	India	
	Near East/Africa	
	South and Central America	
Eff. thermal diffusivity (m²/s)	8E-08	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China