

Covestro Makrolon® 1952 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, Molded , Polycarbonate, Unreinforced, Flame Retardant , Polycarbonate, UV Stabilized

Material Notes:

Main characteristics:• High toughness• Good heat resistance• Glass-like transparency, optical quality• High dimensional accuracy and stability
Grade characteristics:• Flame retardancy• Medium viscosity, easy release• UV stabilized
Formerly Makrolon DP1-1952As of 1 September 2015, Bayer MaterialScience was separated from Bayer AG and officially adopted its new name – Covestro.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Covestro-Makrolon-1952-Polycarbonate.php

Physical Properties	Metric	English	Comments
Bulk Density	0.640 g/cc	0.0231 lb/in ³	pellets; ISO 60
Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183-1
Moisture Absorption at Equilibrium	0.12 %	0.12 %	ISO 62, 50% RH
Water Absorption at Saturation	0.30 %	0.30 %	ISO 62
Water Vapor Transmission	15.0 g/m ² /day @Thickness 0.100 mm	0.966 g/100 in ² /day @Thickness 0.00394 in	85% RH, film; ISO 15106-1
Oxygen Transmission	65.0 cc-mm/m ² -24hr-atm @Thickness 0.100 mm	165 cc-mil/100 in ² -24hr-atm @Thickness 0.00394 in	650 cc/m ² -24hr-bar; film; b.o. ISO 2556
	70.0 cc-mm/m ² -24hr-atm @Thickness 0.0254 mm	178 cc-mil/100 in ² -24hr-atm @Thickness 0.00100 in	2760 cc/m ² -24hr-bar; film; b.o. ISO 2556
Nitrogen Transmission	12.0 cc-mm/m ² -24hr-atm @Thickness 0.100 mm	30.5 cc-mil/100 in ² -24hr-atm @Thickness 0.00394 in	120 cc/m ² -24hr-bar; film; b.o. ISO 2556
	13.0 cc-mm/m ² -24hr-atm @Thickness 0.0254 mm	33.0 cc-mil/100 in ² -24hr-atm @Thickness 0.00100 in	510 cc/m ² -24hr-bar; film; b.o. ISO 2556
Carbon Dioxide Transmission	380 cc-mm/m ² -24hr-atm @Thickness 0.100 mm	965 cc-mil/100 in ² -24hr-atm @Thickness 0.00394 in	3800 cc/m ² -24hr-bar; film; b.o. ISO 2556
	429 cc-mm/m ² -24hr-atm @Thickness 0.0254 mm	1090 cc-mil/100 in ² -24hr-atm @Thickness 0.00100 in	16900 cc/m ² -24hr-bar; film; b.o. ISO 2556

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage, Flow	0.0065 cm/cm @Thickness 2.00 mm	0.0065 in/in @Thickness 0.0787 in	60x60x2 mm; 500 bar; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0070 cm/cm @Thickness 2.00 mm	0.0070 in/in @Thickness 0.0787 in	60x60x2 mm; 500 bar; ISO 294-4
Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Puncture Resistance	5400 N @Temperature 23.0 °C	1210 lb (f) @Temperature 73.4 °F	ISO 6603-2
	6300 N @Temperature -30.0 °C	1420 lb (f) @Temperature -22.0 °F	ISO 6603-2
Ball Indentation Hardness	115 MPa	16700 psi	ISO 2039-1
Tensile Strength at Break	70.0 MPa	10200 psi	50 mm/min; ISO 527-1,-2
Tensile Strength, Yield	66.0 MPa	9570 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	>= 50 %	>= 50 %	Nominal, 50 mm/min; ISO 527-1,-2
	130 %	130 %	50 mm/min; b.o. ISO 527-1,-2
Elongation at Yield	6.1 %	6.1 %	50 mm/min; ISO 527-1,-2
Tensile Modulus	2.40 GPa	348 ksi	1 mm/min; ISO 527-1,-2
Flexural Strength	99.0 MPa	14400 psi	2 mm/min; ISO 178
Flexural Yield Strength	75.0 MPa @Strain 3.50 %	10900 psi @Strain 3.50 %	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	12.0 kJ/m² @Thickness 3.20 mm, Temperature -30.0 °C	5.71 ft-lb/in² @Thickness 0.126 in, Temperature -22.0 °F	complete break; b.o. ISO 180-A
	80.0 kJ/m² @Thickness 3.20 mm, Temperature 23.0 °C	38.1 ft-lb/in² @Thickness 0.126 in, Temperature 73.4 °F	partial break; b.o. ISO 180-A
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179-1eU

Mechanical Properties	Metric	English	Comments
	@Temperature -30.0 °C	@Temperature -22.0 °F	ISO 179-1eU
Charpy Impact, Notched	1.40 J/cm²	6.66 ft-lb/in²	complete break; ISO 7391/b.o. ISO 179-1eA
	@Thickness 3.00 mm, Temperature -30.0 °C	@Thickness 0.118 in, Temperature -22.0 °F	
	7.00 J/cm²	33.3 ft-lb/in²	partial break; ISO 7391/b.o. ISO 179-1eA
	@Thickness 3.00 mm, Temperature 23.0 °C	@Thickness 0.118 in, Temperature 73.4 °F	
Puncture Energy	60.0 J	44.3 ft-lb	ISO 6603-2
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	65.0 J	47.9 ft-lb	ISO 6603-2
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Tensile Creep Modulus, 1 hour	2200 MPa	319000 psi	ISO 899-1
Tensile Creep Modulus, 1000 hours	1900 MPa	276000 psi	ISO 899-1

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	65.0 µm/m-°C	36.1 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
CTE, linear, Transverse to Flow	65.0 µm/m-°C	36.1 µin/in-°F	ISO 11359-1,-2
	@Temperature 23.0 - 55.0 °C	@Temperature 73.4 - 131 °F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	cross-flow; ISO 8302
Hot Ball Pressure Test	135 °C	275 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	136 °C	277 °F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	ISO 75-1,-2
Vicat Softening Point	143 °C	289 °F	50°C/h; ISO 306
	@Load 5.10 kg	@Load 11.2 lb	
	144 °C	291 °F	120°C/h; ISO 306
	@Load 5.10 kg	@Load 11.2 lb	
Glass Transition Temp, Tg	144 °C	291 °F	10°C/min; ISO 11357-1,-2
	V-0	V-0	

Thermal Properties	Metric	English	Comments
Flash Point	460 °C	860 °F	ASTM D 1929
	530 °C	986 °F	self ignition; ASTM D 1929

Optical Properties	Metric	English	Comments
Haze	3.0 %	3.0 %	ISO 14782
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	8.0 %	8.0 %	ISO 14782
	@Thickness 4.00 mm	@Thickness 0.157 in	
Transmission, Visible	84 %	84 %	ISO 13468-2
	@Thickness 4.00 mm	@Thickness 0.157 in	
	88 %	88 %	ISO 13468-2
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093
Dielectric Constant	3.0	3.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.1	3.1	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	34.0 kV/mm	864 kV/in	IEC 60243-1
	@Thickness 1.00 mm	@Thickness 0.0394 in	
Dissipation Factor	0.00080	0.00080	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0090	0.0090	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	125 V	125 V	CTI M; Solution B; IEC 60112
	250 V	250 V	Solution A; IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	300 °C	572 °F	Injection molding; ISO 294
Mold Temperature	80.0 °C	176 °F	Injection molding; ISO 294
Injection Velocity	200 mm/sec	7.87 in/sec	ISO 294

Descriptive Properties	Value	Comments
Electrolytic Corrosion	A1	IEC 60426

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China