

Crucible Steel 174 SXR Precipitation Hardening Stainless Steel

Category: Metal, Ferrous Metal, Stainless Steel, Precipitation Hardening Stainless

Material Notes:

Crucible 174 SXR is a premium quality precipitation- hardening stainless steel designed for use as rifle barrels. It is a modification of Crucible's 17Cr-4Ni which offers substantially improved machinability without sacrificing toughness. Its excellent corrosion resistance approaches that of a 300 series austenitic stainless steel, while its high strength is characteristic of 400 series martensitic stainless steels. At similar hardness levels, Crucible 174 SXR offers greater toughness than either the 410 or the 416 stainless steels which are commonly used for rifle barrels. Information provided by Crucible Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Crucible-Steel-174-SXR-Precipitation-Hardening-Stainless-Steel.php

Mechanical Properties	Metric	English	Comments	
Hardness, Rockwell C	33	33	hardened H1150	
	@Treatment Temp. 621 °C	@Treatment Temp. 1150 °F		
	36	36		
	@Treatment Temp. 579.4 °C	@Treatment Temp. 1075 °F	hardened H1025	
	38	38		
	@Treatment Temp. 551.7 °C	@Treatment Temp. 1025 °F	hardened H1025	
Charpy Impact	54.2 J	40.0 ft-lb	hardened H1025; V-notch	
	@Treatment Temp. 551.7 °C	@Treatment Temp. 1025 °F		
	58.3 J	43.0 ft-lb		
	@Treatment Temp. 579.4 °C	@Treatment Temp. 1075 °F	hardened H1025; V-notch	
	136 J	100 ft-lb		
	@Treatment Temp. 621 °C	@Treatment Temp. 1150 °F	hardened H1150; V-notch	

Component Elements Properties	Metric	English	Comments	
Carbon, C	0.020 %	0.020 %		
Chromium, Cr	15.25 %	15.25 %		
Copper, Cu	3.5 %	3.5 %		
Iron, Fe	75 %	75 %	as balance	



Component Elements Properties	0.60 % Metric	0 60 % English	Comments	
Nickel, Ni	4.8 %	4.8 %		
Niobium, Nb (Columbium, Cb)	0.20 %	0.20 %		
Nitrogen, N	0.015 %	0.015 %		
Phosphorous, P	0.025 %	0.025 %		
Silicon, Si	0.50 %	0.50 %		
Sulfur, S	0.020 %	0.020 %		

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China