

Crucible Steel 214NS (JIS SUH36) Martensitic Steel

Category : Metal , Ferrous Metal , Austenitic , Stainless Steel

Material Notes:

Information provided by Crucible Specialty Metals.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Crucible-Steel-214NS-JIS-SUH36-Martensitic-Steel.php

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	<= 302	<= 302	
Hardness, Rockwell C	<= 42	<= 42	
Tensile Strength, Ultimate	>= 882.6 MPa	>= 128000 psi	
Tensile Strength, Yield	>= 559 MPa	>= 81100 psi	
Elongation at Break	>= 8.0 %	>= 8.0 %	
Reduction of Area	>= 10 %	>= 10 %	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.48 - 0.58 %	0.48 - 0.58 %	
Chromium, Cr	20 - 22 %	20 - 22 %	
Iron, Fe	>= 61.98 %	>= 61.98 %	As Remainder
Manganese, Mn	8.0 - 10 %	8.0 - 10 %	
Nickel, Ni	3.25 - 4.5 %	3.25 - 4.5 %	
Nitrogen, N	0.35 - 0.50 %	0.35 - 0.50 %	
Silicon, Si	<= 0.35 %	<= 0.35 %	
Sulfur, S	0.040 - 0.090 %	0.040 - 0.090 %	

Descriptive Properties	Value	Comments
Heat Treatment, °C	1100-1200 W.Q.; 730-780 A.C.	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China