

DP7-3003 Polyurethane-based Biomedical Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_DP7-3003-Polyurethane-based-Biomedical-Elastomer.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength, Ultimate	25.61 MPa	3714 psi	ASTM D412
Tensile Strength, Yield	7.233 MPa	1049 psi	at 100%; ASTM D412
Elongation at Break	458 %	458 %	ASTM D412
Tear Strength	98.9 kN/m	564 pli	die B; ASTM D624

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China