

DSM Akulon® K224-HG8 (Cond.) 40% Glass Reinforced Nylon 6 (North America) (discontinued **)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, 40% Glass Fiber Filled

Material Notes:

Description: The Akulon portfolio is engineered for optimum performance to suit different processing techniques and end use markets. Unfilled Extrusion Resins Akulon resins are available with melt viscosities to suit all extrusion processes: barrier and coating film, tube and hose, monofilament, stock shapes. Akulon resins are characterized by: consistent quality high purity for film applications, low gel contents. Molding Resins Suited to all engineering demands: Unfilled low and medium viscosity grades Toughened unfilled grades Glass reinforced from 20-45% filled Low warpage reinforced grades Flame retardant; UL V0 rated and glow wire types Halogen free FR grades Blow moldable materials Laser markable resins Laser weldable, high burst pressure grades Toughened, reinforced resins High stiffness grades for metal replacement Akulon Ultraflow resins have high flow with mechanical properties similar to standard materials. Exceptional flow allows: productivity gains in molding lower built in stresses better surface appearances system cost reductions Applications for Molding resins There is an Akulon resin available suitable for any application requiring polyamides. Key areas where DSM has specific application knowledge are Automotive Under the hood and engine components Exterior and interior applications Electrical components and connectors Electrical Low voltage power distribution Lighting Power connectors Consumer Durables Power and lawn and garden tools Small Appliances Sports and leisure equipment Furniture accessories Industrial Goods Transportation (railways) Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Akulon-K224-HG8-Cond-40-Glass-Reinforced-Nylon-6-North-America-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in ³	(DAM); ISO 1183
Water Absorption	5.5 %	5.5 %	(DAM); Sim. to ISO 62
Moisture Absorption at Equilibrium	1.7 %	1.7 %	Humidity Absorption (DAM); Sim. to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	140 MPa	20300 psi	ISO 527-1/-2
Elongation at Break	4.5 %	4.5 %	ISO 527-1/-2
Tensile Modulus	8.50 GPa	1230 ksi	ISO 527-1/-2
Charpy Impact Unnotched	8.50 J/cm ²	40.5 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	11.0 J/cm ²	52.4 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	Metric	English	Comments
	3.40 J/cm ²	16.2 ft-lb/in ²	ISO 179/15A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10°C/min (DAM); ISO 11357-1/-3
UL RTI, Electrical	140 °C	284 °F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 °C	284 °F	UL 746B
	@Thickness 0.710 mm	@Thickness 0.0280 in	
UL RTI, Mechanical with Impact	120 °C	248 °F	UL 746B
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	125 °C	257 °F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical without Impact	140 °C	284 °F	UL 746B
	@Thickness 0.710 mm	@Thickness 0.0280 in	
	150 °C	302 °F	UL 746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	4.4	4.4	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	14	14	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Dissipation Factor	0.11	0.11	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	0.30	0.30	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	400 - 599 V	400 - 599 V	PLC 1; UL 746A

Electrical Properties	500 V Metric	500 V English	IEC 60112 Comments
Descriptive Properties	Value		Comments
Heat stabilized or stable to heat	Yes		
Injection molding	Yes		
Release Agent	Yes		
With Fillers	Yes		

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China