

DSM Arnite® AV2 370 XL PET-GF35

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polyethylene Terephthalate (PET), 40% Glass Reinforced

Material Notes:

35% Glass Reinforced, Low Outgassing

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Arnite-AV2-370-XL-PET-GF35.php

Physical Properties	Metric	English	Comments
Density	1.63 g/cc	0.0589 lb/in ³	ISO 1183
Water Absorption	0.45 %	0.45 %	Sim. To ISO 62
Moisture Absorption	0.180 %	0.180 %	Sim. To ISO 62
Linear Mold Shrinkage, Flow	0.0050 cm/cm	0.0050 in/in	Sim. To ISO 294-4
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	Sim. To ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	185 MPa	26800 psi	ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	ISO 527-1/-2
Tensile Modulus	13.0 GPa	1890 ksi	ISO 527-1/-2
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	25.0 µm/m-°C	13.9 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	40.0 µm/m-°C	22.2 µin/in-°F	ISO 11359-1/-2
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	ISO 75-1/-2

Thermal Properties Deflection Temperature at 1.8 MPa (150 psi)	235 °C Metric	455 °F English	ISO 75-1/-2 Comments
Flammability, UL94	HB	HB	IEC 60695-11-10
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	IEC 60695-11-10
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	3.5	3.5	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.7	3.7	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	33.0 kV/mm	838 kV/in	IEC 60243-1
Dissipation Factor	0.0030	0.0030	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.013	0.013	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 V	250 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China