

DSM Arnite® TV4 241 SL PBT-GF20 FR(17)

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

20% Glass Reinforced, Flame Retardant, UV Stabilized

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Arnite-TV4-241-SL-PBT-GF20-FR17.php

Physical Properties	Metric	English	Comments
Density	1.62 g/cc	0.0585 lb/in ³	ISO 1183
Water Absorption	0.30 %	0.30 %	Sim. To ISO 62
Moisture Absorption	0.150 %	0.150 %	Sim. To ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	110 MPa	16000 psi	ISO 527-1/-2
Elongation at Break	2.5 %	2.5 %	ISO 527-1/-2
Tensile Modulus	8.50 GPa	1230 ksi	ISO 527-1/-2
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.700 J/cm ²	3.33 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C	22.2 µin/in-°F	ISO 11359-1/-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	210 °C	410 °F	ISO 75-1/-2
	V-2	V-2	

Thermal Properties	Metric @ Thickness 0.750 mm	English @ Thickness 0.0295 in	Comments IEC 60695-11-10
	V-0	V-0	IEC 60695-11-10
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	IEC 60093
Dielectric Constant	3.7	3.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	3.9	3.9	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	27.0 kV/mm	686 kV/in	IEC 60243-1
Dissipation Factor	0.0020	0.0020	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.015	0.015	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	250 V	250 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China