

DSM Somos® 7120 Epoxy Photopolymer, UV Postcure (discontinued **)

Category : Polymer , Rapid Prototyping Polymer , Thermoset , Epoxy

Material Notes:

Description DSM Somos® 7120 Photopolymer is a humidity-tolerant, high heat-deflection-temperature, low-curl, high-speed liquid that produces rigid, highly accurate parts. It produces exceptional, undistorted thin walls and down-facing surfaces and exhibits good processing latitude. **Application** Somos® 7120 Photopolymer is used in the solid imaging process to build three-dimensional parts. **Information Provided by DSM Desotech Inc.**

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Somos-7120-Epoxy-Photopolymer-UV-Postcure-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in³	
	@ Temperature 25.0 °C	@ Temperature 77.0 °F	
Viscosity	700 cP	700 cP	
	@ Temperature 30.0 °C	@ Temperature 86.0 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	88	88	ASTM D2240
Tensile Strength, Yield	58.0 MPa	8410 psi	ASTM D638M
Elongation at Break	2.1 - 6.9 %	2.1 - 6.9 %	ASTM D638M
Modulus of Elasticity	2.477 GPa	359.3 ksi	ASTM D638M
Flexural Strength	108 MPa	15700 psi	ASTM D790M
Flexural Modulus	2.967 GPa	430.3 ksi	ASTM D790M
Izod Impact, Notched	0.270 J/cm	0.506 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	<= 70.0 °C	<= 158 °F	ASTM D648

Descriptive Properties	Value	Comments
Appearance	Transparent Amber	
Dp (mm)	0.123	Slope of cure-depth vs. ln(E) curve
E10 (mJ/cm²)	64	Exposure that gives 0.254mm thickness
E5 (mJ/cm²)	23	Exposure that gives 0.127mm thickness

Descriptive Properties	Value	Comments
Ec (mJ/cm2)	0	Critical exposure

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China