

DSM Stanyl® TE250F8 Nylon 46-40% Glass Reinforced (European and Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TE250F8-Nylon-46-40-Glass-Reinforced-European-and-Asian-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.77 g/cc	0.0639 lb/in ³	ISO 1183
Water Absorption	4.5 %	4.5 %	Sim. to ISO 62
Moisture Absorption at Equilibrium	1.3 %	1.3 %	Humidity Absorption; Sim. to ISO 62
Viscosity Test	150 cm ³ /g	150 cm ³ /g	Viscosity Number
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0090 cm/cm	0.0090 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	180 MPa	26100 psi	ISO 527-1/-2
Elongation at Break	1.9 %	1.9 %	ISO 527-1/-2
Tensile Modulus	15.0 GPa	2180 ksi	ISO 527-1/-2
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.00 J/cm ²	28.6 ft-lb/in ²	ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Mechanical Properties	Metric	English	Comments
Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	11.1 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ISO 11359-1/-2
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
CTE, linear, Transverse to Flow	80.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	44.4 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ISO 11359-1/-2
	@Temperature 20.0 $^{\circ}\text{C}$	@Temperature 68.0 $^{\circ}\text{F}$	
Melting Point	295 $^{\circ}\text{C}$	563 $^{\circ}\text{F}$	10 $^{\circ}\text{C}/\text{min}$; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	290 $^{\circ}\text{C}$	554 $^{\circ}\text{F}$	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	290 $^{\circ}\text{C}$	554 $^{\circ}\text{F}$	ISO 75-1/-2
Vicat Softening Point	290 $^{\circ}\text{C}$	554 $^{\circ}\text{F}$	50 $^{\circ}\text{C}/\text{h}$ 50N; ISO 306
Glass Transition Temp, Tg	75.0 $^{\circ}\text{C}$	167 $^{\circ}\text{F}$	Glass Transition Temperature (10 $^{\circ}\text{C}/\text{min}$); ISO 11357-1/-2
UL RTI, Electrical	140 $^{\circ}\text{C}$	284 $^{\circ}\text{F}$	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	140 $^{\circ}\text{C}$	284 $^{\circ}\text{F}$	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
UL RTI, Mechanical with Impact	110 $^{\circ}\text{C}$	230 $^{\circ}\text{F}$	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	125 $^{\circ}\text{C}$	257 $^{\circ}\text{F}$	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
UL RTI, Mechanical without Impact	120 $^{\circ}\text{C}$	248 $^{\circ}\text{F}$	UL746B
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	125 $^{\circ}\text{C}$	257 $^{\circ}\text{F}$	UL746B
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Flammability, UL94	V-0	V-0	IEC 60695-11-10
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	IEC 60695-11-10
	@Thickness 0.350 mm	@Thickness 0.0138 in	
Oxygen Index	37 %	37 %	ISO 4589-1/-2
Glow Wire Test	800 $^{\circ}\text{C}$	1470 $^{\circ}\text{F}$	Glow Wire Ignition Temperature; IEC 60695-2-13
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Thermal Properties	Metric	English	Comments
	925 °C	1700 °F	Glow Wire Ignition Temperature; IEC 60695-2-13
	@Thickness 3.00 mm	@Thickness 0.118 in	
	960 °C	1760 °F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 0.750 mm	@Thickness 0.0295 in	
	960 °C	1760 °F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	IEC 60093
Dielectric Constant	4.0	4.0	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
	4.3	4.3	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Dissipation Factor	0.00060	0.00060	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0016	0.0016	IEC 60250
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	250 - 399 V	250 - 399 V	PLC 2; UL 746A
	350 V	350 V	IEC 60112

Descriptive Properties	Value	Comments
Flame Retardant	Yes	
Flame Retarding Agent	Yes	
Heat stabilized or stable to heat	Yes	
Injection molding	Yes	
Lubricants	Yes	
Platable	Yes	
Release Agent	Yes	
With Fillers	Yes	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China