

DSM Stanyl® TS256F8 Nylon 46-40% Glass Reinforced (Asian Grade) (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

Material Notes:

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedom Stanyl High Flow grades that match the best flowing LCPs while maintaining a high level of mechanical properties Key Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensioners E&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliances Information provided by DSM.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TS256F8-Nylon-46-40-Glass-Reinforced-Asian-Grade-Dry.php

Physical Properties	Metric	English	Comments
Density	1.65 g/cc	0.0596 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	1.2 %	1.2 %	Similar to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	180 MPa	26100 psi	ISO 527-1/-2
Elongation at Break	2.0 %	2.0 %	ISO 527-1/-2
Tensile Modulus	14.0 GPa	2030 ksi	ISO 527-1/-2
Charpy Impact, Notched	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.800 J/cm ²	3.81 ft-lb/in ²	ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	70.0 µm/m-°C	38.9 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	290 °C	554 °F	ISO 75-1/-2
Flammability, UL94	V-0	V-0	IEC 60695-11-10

Thermal Properties	Metric	English	Comments
	@ Thickness 0.750 mm	@ Thickness 0.0295 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China