

DSM Stanyl® TW200F6 (DAM) Nylon 46 30% Glass Reinforced, Heat Stabilized (North America)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Glass Fiber Reinforced

Material Notes:

Information provided by DSM Engineering Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW200F6-DAM-Nylon-46-30-Glass-Reinforced-Heat-Stabilized-North-America.php

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	2.6 %	2.6 %	50% RH / 23°C; Similar to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	210 MPa	30500 psi	ISO 527-1/-2
Elongation at Break	4.0 %	4.0 %	ISO 527-1/-2
Tensile Modulus	10.0 GPa	1450 ksi	ISO 527-1/-2
Charpy Impact Unnotched	8.00 J/cm ²	38.1 ft-lb/in ²	ISO 179/1eU
	7.00 J/cm ²	33.3 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eU
	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 µm/m-°C	11.1 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	295 °C	563 °F	ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	290 °C	554 °F	ISO 75-1/-2

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Volume Resistivity Electrical Properties	1.00e+12 ohm-cm Metric	1.00e+12 ohm-cm English	IEC 60093 Comments
Dielectric Strength	30.0 kV/mm	762 kV/in	IEC 60243-1
Comparative Tracking Index	300 V	300 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China