

## DSM Stanyl® TW275F6 Nylon 46-30% Glass Reinforced, Heat Stabilized, Wear and Friction Modified (Asian Grade) (Cond)

Category: Polymer, Thermoplastic, Nylon, Nylon, Nylon, Ada, Glass Fiber Reinforced

## **Material Notes:**

Stanyl is a high performance polyamide providing good performance and value across a broad range of automotive and electronic applications. Stanyl offers: Highest mechanical properties at high temperatures Excellent resistance to wear and low friction Outstanding flow for easy processing and exceptional design freedomStanyl High Flowgrades that match the best flowing LCPs while maintaining a high level of mechanical propertiesKey Applications: Automotive: Powertrain components, Charge-air coolers, EPS and ETC gears, Motor Sensors, Auto connectors, Chain tensionersE&E: Connectors, Microswitches, Bobbins, Memory modules, Motor components, Industrial, Specialty films and fibers, Consumer appliancesInformation provided by DSM.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_DSM-Stanyl-TW275F6-Nylon-46-30-Glass-Reinforced-Heat-Stabilized-Wear-and-Friction-Modified-Asian-Grade-Cond.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in³	DAM; ISO 1183
Moisture Absorption at Equilibrium	2.6 %	2.6 %	DAM; ISO 1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	ISO 527-1/-2
Elongation at Break	7.0 %	7.0 %	ISO 527-1/-2
Flexural Modulus	6.00 GPa	870 ksi	ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m²	3.81 ft-lb/in <sup>2</sup>	ICO 190/1A
	@Temperature -40.0 °C	@Temperature -40.0 °F	ISO 180/1A
	15.0 kJ/m²	7.14 ft-lb/in <sup>2</sup>	ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	295 °C	563 °F	10°C/min (DAM); ISO 11357-1/-3

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058



Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China