

DSM Stanyl® TW341-B PA46

Category : Polymer , Thermoplastic , Nylon , Nylon 46

Material Notes:

Heat Stabilized, Lubricated

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW341-B-PA46.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	dry; ISO 1183
Moisture Absorption	3.70 %	3.70 %	Sim. To ISO 62
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	Sim. To ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	Sim. To ISO 294-4

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	55.0 MPa	7980 psi	cond; ISO 527-1/-2
	100 MPa	14500 psi	dry; ISO 527-1/-2
	30.0 MPa	4350 psi	ISO 527-1/-2
	@Temperature 200 °C	@Temperature 392 °F	
	35.0 MPa	5080 psi	ISO 527-1/-2
	@Temperature 180 °C	@Temperature 356 °F	
	40.0 MPa	5800 psi	ISO 527-1/-2
	@Temperature 160 °C	@Temperature 320 °F	
	50.0 MPa	7250 psi	ISO 527-1/-2
	@Temperature 120 °C	@Temperature 248 °F	
Elongation at Break	30 %	30 %	dry; ISO 527-1/-2
	>= 50 %	>= 50 %	cond; ISO 527-1/-2
	>= 50 %	>= 50 %	ISO 527-1/-2
	@Temperature 120 °C	@Temperature 248 °F	
	>= 50 %	>= 50 %	ISO 527-1/-2
	@Temperature 160 °C	@Temperature 320 °F	
	>= 50 %	>= 50 %	ISO 527-1/-2
	@Temperature 180 °C	@Temperature 356 °F	

Mechanical Properties	Metric	English	Comments
	@Temperature 200 °C	@Temperature 392 °F	ISO 527-1/-2
Tensile Modulus	1.00 GPa	145 ksi	cond; ISO 527-1/-2
	3.30 GPa	479 ksi	dry; ISO 527-1/-2
	0.500 GPa	72.5 ksi	ISO 527-1/-2
	@Temperature 200 °C	@Temperature 392 °F	
	0.600 GPa	87.0 ksi	ISO 527-1/-2
	@Temperature 180 °C	@Temperature 356 °F	
	0.650 GPa	94.3 ksi	ISO 527-1/-2
	@Temperature 160 °C	@Temperature 320 °F	
	0.800 GPa	116 ksi	ISO 527-1/-2
	@Temperature 120 °C	@Temperature 248 °F	
Flexural Modulus	0.900 GPa	131 ksi	cond; ISO 178
	3.00 GPa	435 ksi	dry; ISO 178
	0.600 GPa	87.0 ksi	ISO 178
	@Temperature 160 °C	@Temperature 320 °F	
	0.800 GPa	116 ksi	ISO 178
	@Temperature 120 °C	@Temperature 248 °F	
Izod Impact Resistance	0.400 J/cm²	1.90 ft-lb/in²	cond; ISO 180/1A
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	0.400 J/cm²	1.90 ft-lb/in²	dry; ISO 180/1A
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	0.900 J/cm²	4.28 ft-lb/in²	dry; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	3.50 J/cm²	16.7 ft-lb/in²	cond; ISO 180/1A
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact Unnotched	NB	NB	cond; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	cond; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Mechanical Properties	^{NB} Metric	^{NB} English	Comments dry; ISO 179/1eU
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	dry; ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.400 J/cm²	1.90 ft-lb/in²	cond; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.400 J/cm²	1.90 ft-lb/in²	dry; ISO 179/1eA
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.900 J/cm²	4.28 ft-lb/in²	dry; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	3.50 J/cm²	16.7 ft-lb/in²	cond; ISO 179/1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	85.0 µm/m-°C	47.2 µin/in-°F	dry; ISO 11359-1/-2
CTE, linear, Transverse to Flow	110 µm/m-°C	61.1 µin/in-°F	dry; ISO 11359-1/-2
Melting Point	295 °C	563 °F	10°C/min; ISO 11357-1/-3
Maximum Service Temperature, Air	152 °C	306 °F	5000 hours Thermal Index; IEC 60216/ISO 27-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	dry; ISO 75-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+9 ohm-cm	1.00e+9 ohm-cm	cond; IEC 60093
	1.00e+14 ohm-cm	1.00e+14 ohm-cm	dry; IEC 60093
Dielectric Strength	10.0 kV/mm	254 kV/in	cond; IEC 60243-1
	20.0 kV/mm	508 kV/in	dry; IEC 60243-1
Comparative Tracking Index	350 V	350 V	dry; IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China