

DSM Stanyl® TW441 (DAM) Nylon 46 High Viscosity, Heat Stabilized, Lubricated (North America)

Category : Polymer , Thermoplastic , Nylon , Nylon 46 , Nylon 46, Unreinforced

Material Notes:

Information provided by DSM Engineering Plastics.

Order this product through the following link:

http://www.lookpolymers.com/polymer_DSM-Stanyl-TW441-DAM-Nylon-46-High-Viscosity-Heat-Stabilized-Lubricated-North-America.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	3.7 %	3.7 %	50% RH / 23°C; Similar to ISO 62

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	100 MPa	14500 psi	ISO 527-1/-2
Elongation at Yield	40 %	40 %	Nominal; ISO 527-1/-2
Tensile Modulus	3.30 GPa	479 ksi	ISO 527-1/-2
Charpy Impact Unnotched	NB	NB	ISO 179/1eU
	NB	NB	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	1.20 J/cm ²	5.71 ft-lb/in ²	ISO 179/1eU
	0.900 J/cm ²	4.28 ft-lb/in ²	ISO 179/1eU
	@Temperature -30.0 °C	@Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
CTE, linear, Transverse to Flow	100 µm/m-°C	55.6 µin/in-°F	ISO 11359-1/-2
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	295 °C	563 °F	ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	190 °C	374 °F	ISO 75-1/-2
Flammability, UL94	V-2	V-2	
	@Thickness 0.750 mm	@Thickness 0.0295 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Dielectric Strength	25.0 kV/mm	635 kV/in	IEC 60243-1
Comparative Tracking Index	400 V	400 V	IEC 60112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China