

Daikin POLYFLON MG-2060 PTFE 30% Graphite Filled Molding Powder

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE

Material Notes:

30% graphite filled. Low friction, excellent chemical resistance, high creep resistance. Applications: Mechanical and chemical service (e.g. bearings, gaskets, packings) Information provided by Daikin Industries.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Daikin-POLYFLON-MG-2060-PTFE-30-Graphite-Filled-Molding-Powder.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.13 - 2.22 g/cc	2.13 - 2.22 g/cc	ASTM D792
Water Absorption	0.00 % @Thickness 8.50 mm, Time 86400 sec	0.00 % @Thickness 0.335 in, Time 24.0 hour	ASTM D570
Viscosity	1.00e+13 - 1.00e+15 cP @Temperature 340 - 380 °C	1.00e+13 - 1.00e+15 cP @Temperature 644 - 716 °F	Melt viscosity
Linear Mold Shrinkage	0.020 - 0.050 cm/cm	0.020 - 0.050 in/in	
Deformation	5.0 %	5.0 %	6.7 MPa load, at 100°C, 24 hrs; ASTM D621
	7.0 %	7.0 %	13.7 MPa load, at 25°C, 24 hrs; ASTM D621

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50 - 65	50 - 65	
Tensile Strength at Break	20.0 - 45.0 MPa	2900 - 6530 psi	ASTM D638
Elongation at Break	200 - 450 %	200 - 450 %	ASTM D638
Tensile Modulus	0.392 GPa	56.9 ksi	ASTM D638
Flexural Modulus	0.490 - 0.588 GPa	71.1 - 85.3 ksi	ASTM D790
Compressive Strength	5.00 - 6.00 MPa @Temperature 25.0 °C	725 - 870 psi @Temperature 77.0 °F	1% deformation; ASTM D695
Izod Impact, Unnotched	1.60 J/cm	3.00 ft-lb/in	ASTM D256
Coefficient of Friction	0.15 - 0.30	0.15 - 0.30	Non-lubricating
Coefficient of Friction, Static	0.020	0.020	Coated-steel surface

Thermal Properties	Metric	English	Comments
CTE, linear	100 $\mu\text{m/m-}^{\circ}\text{C}$	55.6 $\mu\text{in/in-}^{\circ}\text{F}$	ASTM D696
	@Temperature 23.0 - 60.0 $^{\circ}\text{C}$	@Temperature 73.4 - 140 $^{\circ}\text{F}$	
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr-ft ² - $^{\circ}\text{F}$	ASTM C177
Melting Point	327 $^{\circ}\text{C}$	621 $^{\circ}\text{F}$	
Maximum Service Temperature, Air	260 $^{\circ}\text{C}$	500 $^{\circ}\text{F}$	Continuous use
Flammability, UL94	V-0	V-0	
Oxygen Index	$\geq 95\%$	$\geq 95\%$	ASTM D2863

Descriptive Properties	Value	Comments
Chemical Resistance	Excellent	
Contact Angle	110	Angle to level
Weatherability	Excellent	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China