

Denka LCS Z6060 Thermoplastic Elastomer, Injection Molding Grade (general)

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

"DENKA LCS" combines low hardness with a rubber-like texture, having a low permanent compressive distortion/permanent elongation, and is a thermoplastic elastomer that closely resembles vulcanized rubber. It also offers advantages such as a high coefficient of friction, ease of lowering electrical resistance, and good energy-absorbing performance. ApplicationsFor use in automotive components such as weather strips, as well as architectural gaskets, electrical components, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-LCS-Z6060-Thermoplastic-Elastomer-Injection-Molding-Grade-general.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	JIS-Z-8807
Evaporation Loss	7.0 %	7.0 %	JIS-A-5756

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	60	60	JIS-K-6301
Tensile Strength at Break	12.753 MPa	1849.7 psi	JIS-K-6723
Elongation at Break	420 %	420 %	JIS-K-6723
100% Modulus	0.0025506 GPa	0.36994 ksi	JIS-K-6723
Tear Strength	29.4 kN/m	168 pli	kg/cm ² ; JIS-K-6301
Compression Set	39 %	39 %	70°C, 22hrs; JIS-K-6301
	49 %	49 %	100°C, 70hrs; JIS-K-6301

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-38.0 °C	-36.4 °F	JIS-K-6723

Descriptive Properties	Value	Comments
Heating: Retention Rate of Elongation, %	90	100°C x 120 hrs
Heating: Retention Rate of Tensile Strength, %	110	100°C x 120 hrs
Oil Resistance: Retention of Tensile Strength, %	100	70°C x 4hrs; JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	95	70°C x 4hrs; JIS-K-6723
Permanent Set, %, 100%	6	

Permanent Set % 200% Descriptive Properties	12 Value	Comments
--	-------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China