

Denka MALECCA K-095 ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

A heat-resistant ABS resin based on "DENKA IP" – a Styrene-N-Phenylmaleimide copolymer. It has been designed as an easy-to-use resin by improving conventional heat-resistant ABS resins which had defects in terms of moldability, thermal stability, and impact resistance. Applications Mobile phones vehicle-mounted audio equipment automotive interior components home electric appliances OA equipment, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-MALECCA-K-095-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	ASTM D792
Density	1.06 g/cc	0.0383 lb/in ³	ISO 1183
Melt Flow	10 g/10 min @Load 10.0 kg, Temperature 220 °C	10 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	113	113	ISO 2039-2
	114	114	ASTM D785
Tensile Strength at Break	42.0 MPa	6090 psi	ASTM D638
	48.0 MPa	6960 psi	50mm/min; ISO 527-2
Tensile Strength, Yield	38.0 MPa	5510 psi	ISO 527-2
Elongation at Break	29 %	29 %	ISO 527-2
Tensile Modulus	2.50 GPa	363 ksi	1mm/min; ISO 527-1
Flexural Strength	74.0 MPa	10700 psi	15mm/min; ASTM D790
	76.0 MPa	11000 psi	ISO 178
Flexural Modulus	2.35 GPa	341 ksi	15mm/min; ASTM D790
	2.45 GPa	355 ksi	2mm/min; ISO 178
Izod Impact, Notched	2.06 J/cm @Temperature 23.0 °C	3.86 ft-lb/in @Temperature 73.4 °F	ASTM D256
Charpy Impact, Notched	2.10 J/cm ²	9.99 ft-lb/in ²	ISO 179-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C	194 °F	ISO 75-2
	100 °C	212 °F	ASTM D648
Vicat Softening Point	110 °C	230 °F	50N; ISO 306
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China