

Denka REOMER G G3000 Thermoplastic Elastomer, For Extrusion

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Essentially a thermoplastic elastomer with the characteristics of PVC resin and rubber, with excellent rubber-like elasticity. Offers excellent rubbery characteristics, such as permanent compressive distortion, rebound elasticity, etc. compared to soft PVC, and excellent bending strength and ozone resistance compared to rubber.

Applications: Automotive components, door moldings, weather-strips, glass run channels, side bumpers, gaskets, mud flaps, head rests, arm rests, steering wheels, trim, shift bar boots, pedal pads.

Construction material, manufacturing article, home electric, appliance components, gaskets, airtight materials, container packing, packing for vacuum cleaners, hoses, tubes.

For electric wire, appliance cords, cable, tire.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-REOMER-G-G3000-Thermoplastic-Elastomer-For-Extrusion.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	JIS-Z-8807
Evaporation Loss	2.5 %	2.5 %	JIS-A-5756

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55	55	JIS-K-6301
Tensile Strength at Break	9.81 MPa	1420 psi	JIS-K-6723
Elongation at Break	420 %	420 %	JIS-K-6723
100% Modulus	0.002943 GPa	0.4269 ksi	JIS-K-6723
Resilience	34	34	JIS-K-6301

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	-45.0 °C	-49.0 °F	JIS-K-6723

Descriptive Properties	Value	Comments
Heating: Retention Rate of Elongation, %	94	100°C x 120 hrs
Heating: Retention Rate of Tensile Strength, %	106	100°C x 120 hrs
Oil Resistance: Retention of Tensile Strength, %	91	JIS-K-6723
Oil Resistance: Retention Rate of Elongation, %	75	JIS-K-6723

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China