

Denka TE-20 Transparent Resin Polymer (MABS resin) ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

"TX Polymer" (methyl methacrylate styrene), MS resins as an alternative to acrylic resins, with low density, low moisture absorption, and good moldability, "TH Polymer/TP Polymer," MBS resins with a good balance of transparency, strength and fluidity (methyl methacrylate butadiene styrene), "TE Series/CL Series," transparent ABS resins with excellent color attributes and tensile strength are available (among others). Applications TX is used for: flat display substrates optical components miscellaneous goods. TP/TH are used for: food package sheeting as well as in manufacturing electronic equipment and components miscellaneous goods TE/CL are for: electronic equipment and components information equipment components AV equipment, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-TE-20-Transparent-Resin-Polymer-MABS-resin-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Density	1.106 g/cc	0.03996 lb/in ³	ISO 1183
Melt Flow	2.7 g/10 min	2.7 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	33 g/10 min	33 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	57	57	ISO 2039-2
Tensile Strength at Break	34.0 MPa	4930 psi	50mm/min; ISO 527-2
	39.0 MPa	5660 psi	50mm/min; ASTM D638
Elongation at Break	50 %	50 %	50mm/min; ISO 527-2
Flexural Strength	73.0 MPa	10600 psi	ISO 178
Flexural Modulus	2.30 GPa	334 ksi	2mm/min; ISO 178
Charpy Impact, Notched	1.00 J/cm ²	4.76 ft-lb/in ²	ISO 179-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	73.0 °C	163 °F	ISO 75-2
	81.0 °C	178 °F	ASTM D648

Thermal Properties	Metric	English	Comments
Vicat Softening Point	147.11 °C	200 °F	ISO 306, ISO 306
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Haze	2.0 % @Thickness 2.00 mm	2.0 % @Thickness 0.0787 in	ISO 14782
Transmission, Visible	91 % @Thickness 2.00 mm	91 % @Thickness 0.0787 in	ISO 13468-1

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China