

Denka TP-803 Transparent Resin Polymer (MBS resin) Polymethacrylate Butadiene Styrene

Category : Polymer , Thermoplastic , Styrene-Butadiene

Material Notes:

"TX Polymer" (methyl methacrylate styrene), MS resins as an alternative to acrylic resins, with low density, low moisture absorption, and good moldability, "TH Polymer/TP Polymer," MBS resins with a good balance of transparency, strength and fluidity (methyl methacrylate butadiene styrene), "TE Series/CL Series," transparent ABS resins with excellent color attributes and tensile strength are available (among others). Applications TX is used for: flat display substrates optical components miscellaneous goods. TP/TH are used for: food package sheeting as well as in manufacturing electronic equipment and components miscellaneous goods TE/CL are for: electronic equipment and components information equipment components AV equipment, etc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Denka-TP-803-Transparent-Resin-Polymer-MBS-resin-Polymethacrylate-Butadiene-Styrene.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792
Density	1.082 g/cc	0.03909 lb/in ³	ISO 1183
Melt Flow	3.9 g/10 min	3.9 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	
	61 g/10 min	61 g/10 min	ISO 1133
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	29	29	ISO 2039-2
Tensile Strength at Break	32.0 MPa	4640 psi	50mm/min; ISO 527-2
	38.0 MPa	5510 psi	50mm/min; ASTM D638
Elongation at Break	40 %	40 %	50mm/min; ISO 527-2
Tensile Modulus	4.30 GPa	624 ksi	50mm/min; ISO 527-1
Flexural Strength	64.0 MPa	9280 psi	ISO 178
	65.0 MPa	9430 psi	2mm/min; ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	2mm/min; ISO 178
	2.01 GPa	292 ksi	2mm/min; ASTM D790
Izod Impact Resistance	13.7 J/cm ²	65.2 ft-lb/in ²	

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	1.30 J/cm²	5.13 ft-lb/in²	ISO 179-2

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	63.0 °C	145 °F	ISO 75-2
	71.0 °C	160 °F	ASTM D648
Vicat Softening Point	84.0 °C	183 °F	50N; ISO 306
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Haze	2.6 %	2.6 %	ISO 14782
	@Thickness 2.00 mm	@Thickness 0.0787 in	
Transmission, Visible	91 %	91 %	ISO 13468-1
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China